

Technical Data Sheet

EPIKURE™ Curing Agent 530

Product Description

EPIKURE™ Curing Agent 530 is a light color and low viscosity modified cycloaliphatic amine curing agent. This curing agent contains no Nonylphenol.

Application Areas/Suggested Uses

EPIKURE™ Curing Agent 530 is used in formulations of ambient temperature curing compositions such as solvent free coatings, industrial floorings, mortars, primers and adhesives in combination with liquid epoxy resins.

The pot life can be shortened by mixing it with EPIKURE™ Curing Agent 541.

The curing temperature should not fall below +10°C.

Benefits

- Very low viscosity
- Low yellowing characteristics
- Superior surface appearance and blush resistance
- Good mechanical performance

Sales Specifications

Property	Value	Unit	Test Method	Standard
Color	2 max.	Gardner		ISO 4630
Refractive Index at 25°C	1.537 - 1.541		DIN 51423	
Viscosity at 25°C	170 - 230	mPa·s	DIN 53015	

Typical Properties

Property	Value	Unit	Test Method	Standard
Delivery Form	liquid			
Density	1.01 - 1.05	kg/L		ISO 2811
H-Active Equivalent	93	g/equivalent	Calculated	
Recommended Proportion EPIKOTE™ Resin 828 LVEL	50	phr*	Calculated	
Time to T _{max} T _{max} with Epikote™ RESIN 828 LVEL, Starting point 100g Mixture at 23°C	App. 45	min	DIN 16945	

Safety, Storage & Handling

Please refer to the MSDS for the most current Safety and Handling information.

EPIKURE™ Curing Agent 530 should be stored at room temperature in conditions such that moisture is excluded, in the original containers kept tightly closed.

EPIKURE Curing Agent 530
<https://hexioninternet-hexioninternet-slave.azurewebsites.net/en-US/product/epikure-curing-agent-530>

Generated: July 4, 2022
 Issue Date:
 Revision: 4/1/2012 12:00:00 AM

© and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.

Under these conditions the shelf life should be a minimum of two years from date of certification.

EPIKURE Curing Agent 530
<https://hexioninternet-hexioninternet-slave.azurewebsites.net/en-US/product/epikure-curing-agent-530>

Generated: July 4, 2022
Issue Date:
Revision: 4/1/2012 12:00:00 AM

® and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.