

Technical Data Sheet

Astro Mel™ CR-1

Description

Astro Mel CR-1 is a liquid, partially methylated melamine resin.

Application

Astro Mel CR-1 is a waterborne resin that can be used to crosslink hydroxy-functional polymers in formulations used for wood coatings, nonwoven binders, and textile finishing. This resin also readily self-condenses to provide excellent film hardness. In most cases, Astro Mel CR-1 provides adequate cure response without the addition of a strong acid catalyst. To promote cure at lower temperatures, the use of a blocked acid catalyst is recommended.

Benefits

Astro Mel CR-1 can provide improved solvent, stain, mar, and block resistance to wood coatings and firm, resilient finishes that are highly abrasion and solvent resistant in nonwovens and textile applications. Additionally, Astro Mel CR-1 offers good cure response at temperatures below 150 °C, very low formaldehyde content, and good can stability.

Typical Properties

Property	Value	Unit	Test Method
Estimated Storage Life @ 21°C	0		ADCH0473-H
Free Formaldehyde	0.4	%	ADCH0188
Solids	80 ± 2	%	ADCH0407
Solvent Water	0		
Specific gravity	1.23 - 1.25		ADCH0362
Viscosity Gardner-Holdt	Q - V		ADCH0593
Viscosity Brookfield	400 - 700	cP	ADCH0650
Weight	~ 10.3	Pounds per Gallon	ADCH0444

Material Storage

Properties	Method	Specification
Estimated Storage Life @ 21°C	ADCH0473-H	16 weeks

Contact Information

Corporate Headquarters Technical and Sales Inquiries:

180 East Broad Street
 Columbus, OH 43215
 (614) 225-4000
www.hexion.com

Laminates and Melamine Derivatives
 114 Industrial Blvd
 Morganton, NC 28655
 (828) 584-3800 Ext 110

Astro Mel CR-1

<https://hexioninternet-hexioninternet-slave.azurewebsites.net/en-US/product/astro-mel-cr-1>

Generated: May 5, 2024

Issue Date:

Revision:

® and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.

® and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.